

Jantz #3403 - Hissre

1872, 1874, 1875

Duke University Library Conservation Lab
BOOK DOCUMENTATION - SHORT FORM

Lab number: 2008/9-097-100

Date: 28 April 2009

Title: Almanac 5

Author:

Publication date: 1870,
1872, 1874, 1875

Dimensions (cm):
Height
Width
Thickness

Description

Binding Type

- In boards
- Cased
- Laced-case
- Lapped component
- Pamphlet
- Other _____

Primary Covering Material

- Leather ^{1/4}
- Tawed
- Parchment
- Paper
- Cloth
- Other _____

Board Material / Style

- Paper / pulp board
- Wood
- Other _____

Textblock Material

- Paper
- Parchment

Media (multiple)

- Printer's ink
- Manuscript ink
- Graphite
- Color inks
- Pigments / illumination
- Other _____

Leaf Attachment

- Sewn through fold - *onsunkencords*
- Stabbed
- Single leaf /leaves
- Adhesive
- Other _____

Condition

Binding Condition (multiple)

- Red rot - *extreme*
- Board(s) detached
- Spine detached / missing
- Outer joints split
- Inner hinges broken
- Cover detached
- Cover torn
- Cover warped / distorted
- Corners damaged / missing
- Caps damaged / missing
- Previous repair(s)
- Damaging repair(s)
- Sewing broken
- Split textblock
- Other _____

Textblock Damage (multiple)

- Surface dirt
- Minor tears or losses
- Major tears or losses
- Acidic / brittle - *getting brittle*
- Acidic endleaves
- Soft
- Cockling
- Staining / discoloration / foxing - *at edges*
- Loose / detached material
- Insect / pest damage
- Creases / folds
- Ink/Pigment burn
- Flaking ink / pigment
- Mold damage
- Pressure sensitive tape
- Adhesive residue
- Accretions
- Damaging repair(s)
- Other _____

Notes:

Treatment Proposal

Proposed Textblock Treatment (multiple)

- Page repairs / guarding
- Dry cleaning
- Tape / adhesive removal
- Reattach loose leaf/leaves
- Remove mold
- Stain reduction
- Media consolidation
- Flattening
- Interleaving
- Aqueous treatment

Proposed Binding Treatment (multiple)

- Clean / line spine
- Leather consolidation
- Minor structure repair
- Flatten cover / boards
- Repair corners
- Sewing repair
- Board reattachment / reinforcement
- Repair / reinforce inner hinges
- Reback — *remove all leathers + reback in cloth or paper*
- Repair / replace caps
- Reattach case
- New cover / binding
- Disbind
- Resew

Enclosure

- Polyester encapsulation
- Clamshell box (corrugated or cloth)
- Tuxedo box
- Phase box
- Reuse existing enclosure
- Other _____

Treatment Details

Treatment Time Estimate 2.5 hrs each

Proposed By SIGNATURE REDACTED

Approved By SIGNATURE REDACTED

Date 4/29/09

- Photo-documentation required
- No photo-documentation needed

Treatment Report Treated as proposed

Textblock Treatment Performed (multiple)

- Page repaired / guarded — *in some cases w/ toned tissue + wsp*
- Dry cleaned
- Tape / adhesive removed — *son later volumes - removed damaged tips w/ mc positive*
- Loose leaf / leaves reattached
- Mold removed
- Stains reduced
- Media consolidated
- Flattened
- Interleaved
- Washed
- Deacidified
- Re-Sized

Materials / Details

Binding Treatment Performed (multiple)

- Spine cleaned / lined — *wsp + Hanji 1101 tissue that overhangs and is pasted to boards then tawed goat w/ PVA/MC mix 2 layers*
- Leather consolidated
- Minor structure repair
- Cover / boards flattened
- Corners repaired
- Sewing repaired
- Board reattached / reinforced — *then toned tissue w/ a Mc/wsp mix*
- Inner hinges repaired / reinforced
- Rebacked — *tissue*
- Caps repaired / replaced
- Case reattached
- New cover / binding — *see above*
- Disbound
- Resewn — *tissue reback coated w/ SCL 000 + Kivcel G + isopropanol*

Materials / Details

Enclosure

- Polyester encapsulation
- Clamshell box (corrugated or cloth)
- Tuxedo box
- Phase box
- Reused existing enclosure
- Other _____

Treatment Time 3.5 hrs each

Treated By SIGNATURE REDACTED

Date 6/2/09