

Duke University Library Conservation Lab
Baskin Exhibit Book Form

Aeon #: 142 483
Lab: 2017/18-039.030
Date: 2/15/18
Title: *The reason why
the colored American..*
Publication date: 1893

Description

Binding Type

- In boards
- Cased
- Laced-case
- Lapped component
- Pamphlet
- Other _____

Primary Covering Material

- Leather
- Tawed
- Parchment
- Paper
- Cloth
- Other _____

Board Material / Style

- Paper / pulp board
- Wood
- Other NO BOARDS

Textblock Material

- Paper
- Parchment

Media (multiple)

- Printer's ink
- Manuscript ink
- Graphite
- Color inks
- Pigments / illumination
- Other _____

Leaf Attachment

- Sewn through fold
- Stabbed
- Single leaf /leaves
- Adhesive
- Other rusted staples.

Condition

Binding Condition (multiple)

- Red rot
- Board(s) detached
- Spine detached / missing
- Outer joints split
- Inner hinges broken
- Cover detached
- Cover torn
- Cover warped / distorted
- Corners damaged / missing
- Caps damaged / missing
- Previous repair(s)
- Damaging repair(s) - *Poorly tipped to
textblock.*
- Sewing broken
- Split textblock
- Other _____

Textblock Damage (multiple)

- Surface dirt
- Minor tears or losses
- Major tears or losses
- Acidic / brittle
- Acidic endleaves
- Soft
- Cockling
- Staining / discoloration / foxing *from rust.*
- Loose / detached material
- Insect / pest damage
- Creases / folds
- Ink/Pigment burn
- Flaking ink / pigment
- Mold damage
- Pressure sensitive tape
- Adhesive residue
- Accretions
- Damaging repair(s)
- Other _____

Notes:

Treatment Proposal

Proposed Textblock Treatment (multiple)

- Dry cleaning
- Page repairs / guarding
- Tape / adhesive removal
- Reattach loose leaf/leaves
- Media consolidation
- Flattening
- Other:

Remove staples & stitch

Proposed Binding Treatment (multiple)

- Leather consolidation
- Minor structure repair
- Flatten cover / boards
- Repair corners
- Sewing repair
- Board reattachment / reinforcement
- Repair / reinforce inner hinges
- Reback
- Other:

Additional Details

Remove cover, repair/infill as needed. Reattach.

Treatment Time Estimate 1-2 HRS

- Quick Repair Workflow

Proposed By

HH

Approved By

SIGNATURE REDACTED

Date 2/15/18

- Photo-documentation required (DONE 2/28)
- No photo-documentation needed

Treatment Report Treated as proposed

Textblock Treatment Performed (multiple)

- Dry cleaned
- Page repaired / guarded
- Tape / adhesive removed
- Loose leaf / leaves reattached
- Media consolidated
- Flattened
- Aqueous treatment

Binding Treatment Performed (multiple)

- Leather consolidated
- Minor structure repair
- Cover / boards flattened
- Corners repaired
- Board reattached / reinforced
- Inner hinges repaired / reinforced
- Rebacked

Materials / Details

- mechanically removed wrapper & staples.
- guarded pages w/ matsuo kozo #2 (untored) & Artyex P wheat starch paste.
- infilled cover w/ additional layer of 1706 tored w/ Golden Fluid Acryl 2.

Enclosure

- Polyester encapsulation
- Clamshell box (corrugated or cloth)
- Tuxedo box
- Phase box
- Reused existing enclosure
- Other _____

Treatment Time 2 HRS

Treated By

HH

Date

3/2/18

Pre-Loan Changes to Condition: