

TREATMENT PROPOSAL FORM

Call Number: DS124.S325 1878	Lab Number: 2015/16-021	
Library/Department: Rubenstein	Author/Artist: Schleiden, M. J.	
Librarian: Elizabeth Dunn	Title: Die Romantik des Martyriums bei den Juden...	
Date Examined: 7/8/2016	Publication Date: 1878	Numebr of pages: 64
Examined by: Henry Hebert	Size: H 22.0 cm	W 14.5 cm T 0.6 cm
Special instructions:		

Description:

Four-section pamphlet printed on wove paper in black printing ink. No illustrations. Sewn all along onto 2 black textile tapes. Remains of a light brown wove paper tipped to the first and last leaf suggest the text was originally cased into a binding. No other binding materials extant. Currently housed in pamphlet binder with a pocket and sling.

Condition:

Remains of endsheets are small and extremely brittle. Paper has extensive surface dirt, particularly along the top edge. Many pages have cracked along the fold and leaves have become detached. Sewing is weak. Some minor edge tears and dog-eared corners.

Housing in good condition.

Treatment Proposal:

- Completely disband.
- Dry clean pages.
- Mend tears and guard conjugate leaves back together with toned Japanese paper and wheat starch paste.
- Resew and line spine to protect sewing.
- Option 1: Place back in current housing with no further treatment.
- Option 1: Sew on new endsheets and fabricate simple paper case binding.

Estimated Treatment Time: 2 hours

Proposed by:	(signature)	Date:
Approved by:	(signature)	Date:

TREATMENT REPORT FORM

Call Number: DS124.S325 1878	Lab Number: 2015/16-021
Library/Department: Rubenstein	Author/Artist: Schleiden, M. J.
Librarian: E. Dunn	Title: Die Romantik des Martyriums bei den Juden...
Date Examined: 7/8/2016	Publication Date: 1878
Treated by: Henry Hebert	Size: H 22.0 cm W 14.5 cm T 0.6 cm
Special instructions:	

Treatment Performed:

- Before and after written and photographic documentation was produced.
- Dry cleaned pages with vulcanized rubber sponges.
- Applied 4% Culminal MC 2000 S Methylcellulose (Talas) in deionized (DI) water poultice to remove remains of colored wove paper attached to the front cover.
- Cut and removed remaining sewing.
- Guarded folios and mended pages as required with pre-toned Tengujo Japanese paper (Japanese Paper Place) and Aytex-P wheat starch paste.
- Resewed through the fold using an unsupported, 2-hole pamphlet stitch with unbleached 35/3 linen thread using original sewing stations.
- Pasted up spine and lined with untoned Hanji 1308 (Polistini) to consolidate textblock and protect exposed thread.
- Placed back in pamphlet binder with paper sling for safe handling.

Total Hours: 2 hours

Treated by:	(signature)	Date:
--------------------	--------------------	--------------